

Properties		Test Method	12 mil B/B
Appearance			Black
Thickness (Nominal)		ASTM D 1777	12 mil
Mass per Unit Area		ASTM D 751	6.2 oz/yd <sup>2</sup>
Hydrostatic Resistance		ASTM D 751	81 psi
Mullen Burst Strength		ASTM D 3786	330 psi
Puncture Resistance		ASTM D 48333	78 lbs
Grab Tensile Strength	MD	ASTM D 751	179 lbs
	TD		154 lbs
Tongue Tear	MD	ASTM D 751	56 lbs
	TD		50 lbs

MD = Machine Direction

TD = Transverse Direction

B/B = Black/Black Fabric Color

Values are +/- 10% and are typical data, not intended as limiting specifications.

UV Accelerated Weathering

More than 90% strength retained after 2,000 hours exposure