

Properties		Test Method	16 mil B/B
<b>Appearance</b>			Black
<b>Thickness (Nominal)</b>		ASTM D 1777*	16 mil
<b>Mass per Unit Area</b>		ASTM D 751	7.5 oz/yd <sup>2</sup>
<b>Hydrostatic Resistance</b>		ASTM D 751	124 psi
<b>Mullen Burst Strength</b>		ASTM D 3786	391 psi
<b>Puncture Resistance</b>		ASTM D 4833	95 lbs
<b>Grab Tensile Strength</b>	Warp	ASTM D 751	191 lbs
	Weft		201 lbs
<b>Tongue Tear</b>	Warp	ASTM D 751	58 lbs
	Weft		57 lbs

B/B = Black on both sides

UV Accelerated Weathering. More than 90% strength retained after 2,000 hours exposure.

\*ASTM 1777 Option 1

All Values are +/- 10% and are not intended as limiting specifications.

DISCLAIMER: The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for application is the sole responsibility of the user. These values are based on testing results from past fabric runs. Each production run varies in final results. If a certain specified value is required, please inform us in advance and we can provide current testing results.