

Properties		Test Method	20 mil B/B
Appearance			Black
Thickness (Nominal)		ASTM D 1777*	20 mil
Mass per Unit Area		ASTM D 751	9.4 oz/yd ²
Hydrostatic Resistance		ASTM D 751	160 psi
Mullen Burst Strength		ASTM D 3786	457 psi
Puncture Resistance		ASTM D 4833	126 lbs
Grab Tensile Strength	Warp	ASTM D 751	235 lbs
	Weft		225 lbs
Tongue Tear	Warp	ASTM D 751	59 lbs
	Weft		63 lbs

B/B = Black on both sides

UV Accelerated Weathering. More than 90% strength retained after 2,000 hours exposure.

*ASTM 1777 Option 1

All Values are +/- 10% and are not intended as limiting specifications.

DISCLAIMER: The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for application is the sole responsibility of the user. These values are based on testing results from past fabric runs. Each production run varies in final results. If a certain specified value is required, please inform us in advance and we can provide current testing results.