

| Properties | | Test Method | 30 mil B/B or W/B |
|-------------------------------|------|--------------|-------------------------|
| Appearance | | | Black or White |
| Thickness (Nominal) | | ASTM D 1777* | 34 mil |
| Mass per Unit Area | | ASTM D 751 | 21.8 oz/yd ² |
| Hydrostatic Resistance | | ASTM D 751 | 173 psi |
| Mullen Burst Strength | | ASTM D 3786 | 222 psi |
| Puncture Resistance | | ASTM D 4833 | 87 lbs |
| Grab Tensile Strength | Warp | ASTM D 751 | 242 lbs |
| | Weft | | 241 lbs |
| Tongue Tear | Warp | ASTM D 751 | 50 lbs |
| | Weft | | 63 lbs |

B/B = Black on both sides

W/B = White on one side, black on the other

UV Accelerated Weathering. More than 90% strength retained after 2,000 hours exposure.

*ASTM 1777 Option 1

All Values are +/- 10% and are not intended as limiting specifications.

DISCLAIMER: The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for application is the sole responsibility of the user. These values are based on testing results from past fabric runs. Each production run varies in final results. If a certain specified value is required, please inform us in advance and we can provide current testing results.