

Properties		Test Method	30 mil B/B or W/B
<b>Appearance</b>			Black or White
<b>Thickness (Nominal)</b>		ASTM D 1777*	46 mil
<b>Mass per Unit Area</b>		ASTM D 751	22.6 oz/yd <sup>2</sup>
<b>Hydrostatic Resistance</b>		ASTM D 751	189 psi
<b>Mullen Burst Strength</b>		ASTM D 3786	187 psi
<b>Puncture Resistance</b>		ASTM D 4833	87 lbs
<b>Grab Tensile Strength</b>	Warp	ASTM D 751	273 lbs
	Weft		267 lbs
<b>Tongue Tear</b>	Warp	ASTM D 751	57 lbs
	Weft		73 lbs

B/B = Black on both sides

W/B = White on one side, black on the other

UV Accelerated Weathering. More than 90% strength retained after 2,000 hours exposure.

\*ASTM 1777 Option 1

All Values are +/- 10% and are not intended as limiting specifications.

DISCLAIMER: The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for application is the sole responsibility of the user. These values are based on testing results from past fabric runs. Each production run varies in final results. If a certain specified value is required, please inform us in advance and we can provide current testing results.