

Properties		Test Method	30 mil B/B
Appearance			Black
Thickness (Nominal)		ASTM D 1777*	30 mil
Mass per Unit Area		ASTM D 751	12.1 oz/yd <sup>2</sup>
Hydrostatic Resistance		ASTM D 751	248 psi
Mullen Burst Strength		ASTM D 3786	632 psi
Puncture Resistance		ASTM D 4833	147 lbs
Grab Tensile Strength	Warp	ASTM D 751	357 lbs
	Weft		341 lbs
Tongue Tear	Warp	ASTM D 751	81 lbs
	Weft		81 lbs

B/B = Black on both sides

UV Accelerated Weathering. More than 90% strength retained after 2,000 hours exposure.

\*ASTM 1777 Option 1

All Values are +/- 15% and are not intended as limiting specifications.

DISCLAIMER: The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for application is the sole responsibility of the user. These values are based on testing results from past fabric runs. Each production run varies in final results. If a certain specified value is required, please inform us in advance and we can provide current testing results.